



The color samples below are approximations only. Jobsite applied colors will vary from this color card due to printing variances as well as the texture and porosity of the substrate. UNITED COATINGS recommends applying a color sample to an inconspicuous area on the actual substrate to verify color choice.

UNITED COATINGS - Spokane Valley, WA • Tempe, AZ • (509) 926-7143 • (800) 541-4383 • Fax (509) 928-1116 • www.unitedcoatings.com

* These estimates are totals for two separate applications. Apply approximately half the total number of gallons in each of the two coats. The above absorption (coverage) rates are provided for estimating purposes only. Coverage rates will vary with texture and porosity of the substrate. Allow for additional material when estimating coverage over highly textured or porous surfaces.

ESTIMATED COVERAGE RATES*

Substrate _____ Square Feet/Gallon
Concrete/Asphalt 200 to 250 (4.9 to 6.1 m²/l)

- Apply to concrete, masonry or asphalt
- UV resistant
- Non-skid texture or smooth
- Abrasion resistant
- Resist motor oils and gasoline
- Soap and water cleanup

ADVANTAGES



Every bucket offers "PROTECTION FROM WITH-IN"



RHINO TOP is a high quality water-based acrylic finish incorporating an epoxy additive to increase the abrasion resistance properties of the film. A special spherical silica sand is suspended in the emulsion to provide a fine uniform texture. This silica can be eliminated for projects requiring a smooth finish.

RHINO TOP provides a durable colored topping for horizontal concrete and asphalt surfaces. In addition, its satin sheen makes **RHINO TOP** an aesthetically pleasing wall dressing that effectively evens out texture and color variations over various concrete substrates.

- PATIOS
- WALKWAYS
- OUTDOOR SPORT COURTS
- POOL DECKS
- HIGHWAY STRUCTURES
- EXTERIOR WALLS & MORE!

SURFACE PREPARATION

Concrete: All smooth troweled concrete surfaces must be acid etched prior to coating. Broom finished concrete must be clean and dry. Remove any foreign materials such as curing agents, grease or oil with a concentrated commercial detergent. Prepare the surface to be coated by thoroughly cleaning with a power vacuum or compressed air. Immediately following final cleaning, apply a concrete sealer such as **Uniseal** from UNITED COATINGS. After the sealer has dried, repair cracks wider than a hairline with high quality acrylic or single component urethane caulk.

Asphalt: Allow new asphalt surfaces to cure for a minimum of 60 days prior to application. Clean the surface completely with a commercial grade detergent and rinse thoroughly with plenty of clean water.

APPLICATION

Surface preparation is the most important phase of the application process. Please refer to the product label and Technical Data Sheet for complete surface preparation instructions.

RHINO TOP Smooth can be applied by airless or conventional spray, brush or roller. **RHINO TOP Textured** must be applied by roller. Apply 2 coats at the rate of 200 to 250 sq. ft. per gallon (4.9 to 6.1 m²/l) per coat. Allow a minimum of 2 hours drying time between coats. The second coat should be applied in a perpendicular direction to the first coat. Consult the Technical Data Sheet for detailed instructions.

"Rhino Top is also a great way to mark walkways on flat roofs !"

