

Certificate of Analysis

Taber Abrasion

Product Name	Elastuff 300
Batch Number	Part A: 97881, Part B: 97880
Manufacture Date	21 May 04
Test Date	25 Aug 04
Application/Date	10 June 04 / 160° F. material temperature at 3000 psi pump pressure.
Test Method	ASTM D-4060 Abrasion Resistance of Organic Coatings by the Taber Abraser
Test Conditions	As per ASTM standard. Any deviation reported at end of certificate.

This certificate confirms that the above product was tested as per stated standard specification using calibrated equipment and qualified staff. The following test results were obtained.


Test Results

Parameter	Wheel	Average Wear Index
Taber Abraser	H 10	0.08

Test conditions (if different from standard test conditions) and/or notes.

Average wear index represented as grams per 1000 cycles.
 Taber Abraser wheels/load used: H-10 / 1000g.
 Abrasion disks cut from spray out sheet.
 Results represent average of 2 samples.

Results witnessed and verified by a technical representative of GeoEngineers, Inc.



Reviewed by:
 Timothy D. Barber